




**Appearance & Shape:** To be free from any defect such as flow, burrs, unevenness etc; as per IEC standards

**Effective parameters irrespective of material grade (per set)**


Parameter	Value	Unit
Effective Length ( $L_e$ )	50.5	mm
Effective Area ( $A_e$ )	30.7	mm <sup>2</sup>
Effective Area ( $A_{Min}$ )	30.1	mm <sup>2</sup>
Effective Volume ( $V_e$ )	1550	mm <sup>3</sup>
Approx. Weight (without gap)	7.65	g/set



**EE2005A Un-gapped (OL)**

**Test Conditions: 1kHz/1mT/CFR COIL,N=100/25°C**

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)/Set	$P_v$ (W/set)	Ordering code
CF292	1800 ±20%	1150 +30%/-20%	≤0.18 (100mT,100kHz,100°C)	CF292 EE2005A OL
CF139	2100 ±20%	1300 +30%/-20%	≤0.15 (100mT,100kHz,100°C)	CF139 EE2005A OL
CF297	2300 ±20%	1400 +30%/-20%	≤0.14 (100mT,100kHz,100°C)	CF297 EE2005A OL
CF124	2500 ±20%	1500 +30%/-20%	≤0.23 (200mT,25kHz,100°C)	CF124 EE2005A OL



Remarks: Value of "G" is Zero (0) for Un-Gapped Cores, for Gapped Cores the value of "G" varies as per the Gap/AL value

For general terms and conditions please visit

[http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6\\_GTC.pdf](http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6_GTC.pdf)

**Regd. Office & Works: Jabli, Distt. Solan, Himachal Pradesh – 173 209 (India)**

**E-mail: sales@cosmoferrites.com**